

MATERIAL SAFETY DATA SHEET

(Approved by U.S. Department of Labor as "Essentially Similar" to Form OSHA-20)

MSDS AS 003 DATE 6/5/79

PAGE 1

1 PPOD	LICT IDENTIFICATION				
	UCT IDENTIFICATION	N			
CHEMICAL NAME AND SYNONYMS N.A.			REGULAR TELEPHONE NO. 302—575-5000 CHEMTREC TELEPHONE NO. 800—424-9300		
CHEMICAL FAMILY Amine cured epoxy/graphite			CAS NO.	N.A.	
FORMULA N.A.			MOLECULAR WEIGHT		
TRADE NAME AND SYNONYMS 3501-	6/AS, HM or HT, Graph	ite/Epoxy	Prepreg		
	RDOUS INGREDIENTS				
MATERIAL			11.00	TLV-TWA VALUES ADOPTED BY ACGIH	
Uncured multifunctional epoxy resins SEP0498: Not established.					
III. PHYSICAL DATA					
BOILING POINT, 760 mm Hg	N.A.	ENERHING	POINT	N.A.	
VAPOR PRESSURE @	N.A.	SPECIFIC (H <sub>2</sub> O=1)	GRAVITY	№ 1.493	
VAPOR DENSITY (AIR=1)	N.A.	PERCENT BY VOLUM	VOLATILE ME (%)	< 1%	
SOLUBILITY IN WATER, % BY WEIGHT @	Negligible		TION RATE CETATE=1)	N.A.	
APPEARANCE AND ODOR:  Resin impregnated graphite fiber on carrier paper. No odor.					
IV. FIRE AND EXPLOSION HAZARD DATA					
FLASH POINT Polymeri (TEST METHOD) point.	zes below flash	AUTOIGNIT		_	
FLAMMABLE LIMITS IN AIR PERCENT BY VOLUME	LOWER	TENII ENAT	UP		
EXTINGUISHING MEDIA:	N.A.		L	N.A.	
SPECIAL FIRE-FIGHTING PROC	arbon dioxide, dry ch EDURES:	emical, w	ater.		
Use self-contained l	oreathing apparatus o	r fresh a	ir mask.		
UNUSUAL FIRE AND EXPLOSION	ON HAZARDS:				
N.A. NOTES: NA = NOT APPLICABLE					
N.A.					

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

HERCULES INCORPORATED · WILMINGTON, DELAWARE 19899

HER. 24440 9-78 IM 82208H

PRINTED IN U.S.

DATE 6/5/79

PAGE 2

V. HEALIH HAZARD DATA				
THRESHOLD LIMIT VALUE: Not established.				
EFFECTS OF OVEREXPOSURE:				
Possible skin sensitization to personnel allergic to epoxy compounds.				
EMERGENCY AND FIRST AID PROCEDURES:				
Emendend Alb Fillor Alb Fillocebolics.				
Skin: Remove from exposure. Wash thor persists, get medical attention.	oughly with soap and water. If allergy			
And the state of t				
VI. REACTIVITY DATA				
STABILITY CONDITIONS TO AVOID: \$10w	reaction at room temperature.			
UNSTABLE				
STABLE X Avoid high temperatures	in large confined volume of product.			
INCOMPATIBILITY (MATERIALS TO AVOID Strong oxidizers.				
HAZARDOUS DECOMPOSITION PRODUCTS: Oxides	of nitrogen. Carbon and Sulfur.			
	TIONS TO AVOID:			
POLYMERIZATION WILL NOT OCCUR	Temperature > 275°F			
VII. SPILL OR LEAK PROCEDURES				
STEPS TO BE TAKEN IF MATERIAL IS RELEASED OR SPILLED:				
Place in sealed plastic bags for disposal.				
WASTE DISPOSAL METHOD:	Diagon of in accordance with Palauri Chan-			
Do not incinerate. Dispose of in accordance with Federal, State, and local laws and regulations.				
VIII. SPECIAL PROTECTION I	NFORMATION			
RESPIRATORY PROTECTION				
(SPECIFY TYPE) Not needed for no				
VENTILATION LOCAL EXHAUST	SPECIAL			
MECHANICAL (GENERAL)	OTHER			
PROTECTIVE CLOVES.	Adequate ventilation. EYE PROTECTION:			
OTUER PROTECTIVE FOURNISHED	LIET HOTECHON:			
None				
IX. SPECIAL PRECAUTIONS				
PRECAUTIONARY LABELING:				
WARNING: MAY CAUSE MINOR SKIN IRRITATION. Avoid prolonged or repeated contact with				
skin. Wash thoroughly after l	handling.			
777.00				
FIRST AID: Remove from exposure. Wash thoroughly with soap and water. If allergy persists, get medical attention.				
This product is electrically conductive.				
OTHER HANDLING AND STORAGE CONDITIONS:				
Store a	at or below 0°F in sealed containers for			
maximu	m stability. DO NOT INCINERATE.			

PRINTED IN 11 6.4